

### Sublisheet 200



#### **Artwork**

As the Sublisheet 200 is printed directly onto do not mirror your artwork.

#### **Printing**

Place the sheet directly into your sublimation printer. Print on the textured side of sheet.

If using Print & Cut technique, print directly from your cutter's software to the dye sublimation printer, making sure registration marks are on the sheet. (If using a Cricut or Cameo a deep cut blade works best, using a flock setting.)

If print and cut is not required, print from your dye sublimation printer software. The design can be cut around using scissors, or trimmed with a craft knife.

#### **Pre Application**

Place print on your heat press, cover with silicone paper and press, at 170°c for 15 seconds. This is to fix the colours in the design and reduce fading when on the garment.

#### **Application**

- 1 Press the garment for 5 seconds to flatten and remove any excess moisture.
- 2 Remove the print from the backing and place on the garment, print side facing up. Place a teflon sheet or silicone paper over the print.
- 3 Using a medium to high pressure press for 50 seconds at 170°c.

## **Washing & Aftercare**

Wait 24 hours before the first wash.

Machine washable up to 60°c and wash inside out. Do not use bleach or harsh washing detergents.

Iron only inside out on the reverse. Suitable for tumble drying. Do not dry clean

## Siser Easysubli





# **APPLICATION INSTRUCTIONS**

⊘ Applies On	SUGGE	STED CUTTING	G SETTINGS	TRANSFER SETTING			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
	45°	120 gf	20 cm/sec	15 seconds	<b>155°C</b> (311°F)	Medium (2,5/3,5 bar)	hot

- Print, cut, and weed material
- Remove the print from the carrier by hand and place it on the garment
- Cover the print with silicon or parchment paper
- Heat apply at the conditions shown above
- \*TTD Special application tape is required when designs have multiple pieces that need to be kept in alignment
- Peel it hot

# CARE AND WASHING RECOMMENDATIONS

₩ Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	<b>∮</b> ⊳ Position
Up To 60°C inside-out	YES best inside-out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents